

Dimension board

| | |
|---------------------|--------------------|
| LENGTH | 2200 mm |
| WIDTH | 240 mm |
| TOTAL THICKNESS | 15.0 mm |
| THICKNESS TOP LAYER | 4 mm |
| LAYER CONTENTS | Min 3 Pl x 2200 mm |

Dimension pack

| | |
|----------------------|---------------------|
| PACK LENGTH | 2210 mm |
| PACK WIDTH | 270 mm |
| PACK THICKNESS | 80 mm |
| PACK WEIGHT | 20 kg |
| LAYERS/BOX | 5 |
| M ² /PACK | 2.64 m ² |

Dimension pallet

| | |
|------------------------|-----------------------|
| PALLET LENGTH | 2230 mm |
| PALLET WIDTH | 1080 mm |
| PALLET HEIGHT | 820 mm |
| PALLET WEIGHT | 800 kg |
| PACKS/PALLET | 48 |
| M ² /PALLET | 137.40 m ² |

CHARACTERISTICS

Top layer

| | |
|---------------------|--------------------|
| WOOD SPECIES | Oak |
| LATIN NAME | Quercus Robur |
| GRADE | CLASSIC B |
| CONSTRUCTION | 2-layer |
| THICKNESS TOP LAYER | 4 mm |
| PATTERN | 1 strip |
| CUTTING METHOD | Zaagfineer |
| BEVEL | 4 sides aged bevel |
| FINISH | Oil |
| SURFACE STRUCTURE | Structured |

Composition of the support

| | |
|-------------------------|----------------------|
| SUPPORT TYPE | MPX |
| WOOD SPECIES SUPPORT | Mixed Light Hardwood |
| TOTAL THICKNESS SUPPORT | 11 mm |
| ADHESION | Kruiselings |

Installation

| SYSTEM | APPLICATIONS | UNDERFLOOR HEATING |
|-------------------|--|--------------------|
| Tongue and groove | Light household use. Moderate commercial use. Normal commercial use. Normal household use. Intensive commercial use. | Yes |
| | | RE-SANDABLE |
| | | Yes |
| | | |

TECHNICAL SPECIFICATIONS

| | Norm | Result |
|-----------------------|---------------------|------------------------|
| REACTION TO FIRE | EN 13501-1 | Dfl-S1 |
| FORMALDEHYDE EMISSION | EN 717-1 | E1 |
| PCP | CEN/TR 14823 | ≤ 5ppm |
| THERMAL CONDUCTIVITY | EN 12667 / ISO 8302 | 0,11m ² k/w |
| BIOLOGICAL DURABILITY | EN 335 | Class 1 |
| BREAKING STRENGTH | EN 1533 | Pass |
| SLIPPERINESS | EN 15676 | Pass |
| MOISTURE CONTENT | EN 13183-1 | 7% (+/-2%) |

CERTIFICATION



EN 14342

